



LABPOX 35

100% Solids, High Performance Epoxy for Industrial Applications

Description

The LABPOX 35 is an epoxy system specifically designed for industrial applications and porous concrete slabs. The product is 100% solids two components (2A:1B) epoxy floor coating system which is virtually VOC-free. This product possesses superior mechanical properties best suited for industrial applications but can also be used for commercial and residential applications. The LABPOX 35 offers a long pot life and working time. It has been designed as a topcoat epoxy but it is self-priming. For heavy traffic applications, we recommend using Labsurface's EPOXY PRIMER prior the installation. The LABPOX 35 formulation is based on a high-performance cycloaliphatic polyamine technology displaying outstanding properties and superior finish.

Uses

The LABPOX 35 provides excellent results for the most demanding applications:

- + Industrial, commercial, and residential uses
- + Porous concrete slabs
- + Manufacturing facilities
- + Warehouses
- + Commercial centers
- + Office buildings
- + Retail stores
- + Garages
- + Food/beverage processing and preparation plants
- + Public facilities including hospitals and schools
- + Pharmaceutical companies

Advantages

- + Ideal for industrial applications and porous concrete slabs
- + Reduce pin holes
- + Best-in-class in the industry for resistance to contaminants (fish eyes)
- + Possible to sand the product after 10 hours (non-sticky)
- + Environment friendly (100% solids, VOC-free and no solvent)
- + Virtually odor free
- + Potential for LEED eligibility
- + Easy application with long pot life and working time (45 minutes)
- + Superior mechanical and chemical properties suited for the toughest industrial applications
- + Good elongation and excellent abrasion resistance
- + High resistance to amine blush
- + Impermeability / low moisture sensitivity

- + High density of the product prevents dirt penetration resulting in low maintenance post application
- + Available in unlimited color range

Application Data

Mix Ratio	2A:1B	
Packaging	3 US gallon kit (3 x 3.78L) 15 US gallon kit (3 x 18.9L)	
Color	Colored	
Solids Coverage / US GAL	<u>Mils</u>	<u>Sq. Ft.</u>
	8	200
	10	160
	12	133
	16	100
	20	80
Shelf Life	One year, in original unopened factory pails under normal storage conditions	
Substrate temp.	Min 16°C / 61°F, Max 30°C / 86°F	
Cure Time		
Working time	45 min	22°C / 72°F and 30% Rel. Hum.
Tack Free	5 hours	22°C / 72°F and 30% Rel. Hum.
Recoat Time	5-24 hours	22°C / 72°F and 30% Rel. Hum.
Dry Through (Sandable)	10 hours	22°C / 72°F and 30% Rel. Hum.
Foot Traffic	24 hours	22°C / 72°F and 30% Rel. Hum.
Light Traffic	24 hours	22°C / 72°F and 30% Rel. Hum.

Technical Properties

Hardness	ASTM D2240	80	Shore D
Viscosity		1100/1200	cps
Solids Content		100%	
Sandability to dust		10	hours
VOC Content		0	g/l

Surface Preparation

Concrete should be clean, dry and free of grease, oil, paint, curing agents or any contaminants that may inhibit proper adhesion. Concrete should be cured at least 28 days before applying the coating system. If the concrete slab has been installed within 28 days, the LABPOX MVB moisture mitigation system can be considered (refer to the LABPOX MVB technical data sheet for additional details).

Proper testing procedures should be practiced with regards to soil acidity and moisture vapor transmission. Take a pH reading to ensure concrete is neutral (a reading between 5 and 9 is acceptable).



LABPOX 35

100% Solids, High Performance Epoxy for Industrial Applications

Use a Tramex® CME / CMExpert to measure the moisture content of the concrete slab. Moisture content must be below 4% before applying the product. It is necessary to take several measurements at various places on the slab. If the reading is higher than 4%, steps will be required to neutralize the soil moisture. The first thing to do is to make sure that the floor is completely dry before application. Floors with higher results can receive the LABPOX MVB moisture mitigation.

Surface must be shot blasted or prepared with an equivalent mechanical means in line with CSP-2 or more depending on the application. Ensure the surface is free of contaminants, and the pores are open to allow the product to penetrate.

If the product is applied over an existing LABPOX flooring system that has been cured for a period longer than 24 hours, it should be sanded with a proper floor machine. A mechanical bond to a sanded surface is required and the pores of the existing coating must be opened for better adhesion. Vacuum dust and properly wipe the surface with alcohol or solvent prior applying the LABPOX 35. The alcohol or solvent must be completely evaporated before applying the product. This preparation is necessary to ensure proper adhesion. Conduct adhesion tests if there is a doubt about surface preparation.

Mixing

Before final mixing, pre-mix part A at low speed using a Jiffy® or an Exomixer® mixer blade. Pigments may have separated from the rest of the formulation during storage. Mixing should be done until the color is uniform. The LABPOX 35 is only available in pre-tinted colors.

Then, using a Jiffy® or an Exomixer® mixer blade, mix two parts of A and one part of B together at low speed in a separate container. The mixing container must be clean and free of any outside particles. Mix thoroughly for a minimum of three minutes, until a completely homogeneous mixture is obtained. Use a low-speed drill (300-450 rpm) to minimize air entrapment. It is recommended to activate the mixer in the reverse mode after the first 90 seconds for the liquid to mix from the bottom of the mixing can to the top. Make sure to scrape sides and bottom of mixing container so no unmixed material remains. Mix only the necessary quantity to be used according to the specified pot life / working time.

Application

Apply only when air and slab temperature is between 16°C / 61°F - 30°C / 86°F and the relative humidity of less than 85%. If a heated floor is installed, ensure that the system is turned off 2-4 hours (depending on type of radiant floor) before application and for the

full duration of the cure. The product has been designed to adhere to concrete surfaces.

The LABPOX 35 is self-priming. Apply the first coat with a squeegee in thin coat and back roll to properly seal the surface. If the concrete is porous, we suggest a tight squeegee, no back roll. If there is appearance of pin holes during the application, allow sufficient time to go back and either burst the pin holes by rolling back and forth or with another squeegee pass. The LABPOX 35 has been formulated to reduce the occurrence of pin holes, however if the slab is very porous and there is a significant presence of pinholes after applying the first coat, sand and plug the pinholes with epoxy gel.

For the second coat, squeegee and back roll the product to the desired thickness. It is recommended to apply the product in a multi-directional (north-south, east-west) motion to ensure proper coating thickness.

For standard systems, we recommend the application of one base coat and one topcoat for total system thickness of approximately 20 mils.

For high traffic applications, it is recommended to use Labsurface's EPOXY PRIMER before installing the LABPOX 35. The EPOXY PRIMER will seal the slab and display higher flexibility. A thickness of 4-6 mils is recommended for the EPOXY PRIMER. Labsurface's EPOXY PRIMER cures within 4 hours under normal conditions while providing a working time of 45 minutes (refer to the EPOXY PRIMER TDS, or contact us for more details).

For better stain and chemical resistance, we strongly recommend the usage of a AQUALAB PUR, LABFAST or LABSHIELD product over the LABPOX 35 or over any epoxy product other than a Novolac epoxy. In addition to the superior chemical resistance and cleanability, the matte version of the AQUALAB PUR MATTE possesses a unique characteristic which is to make the scratches less apparent. The AQUALAB PUR, LABFAST or LABSHIELD products also provide additional UV protection that will significantly slow the yellowing of epoxy.

Recoat

Do not recoat without sanding if last coating of the product has been applied for more than 24 hours. The floor surface should be sanded/abraded until a uniform dullness is achieved. There should be no gloss on the prior coating after vacuuming and before applying the next coat.



LABPOX 35

100% Solids, High Performance Epoxy for Industrial Applications

Limitations

Requires a dry substrate Moisture content of the substrate must be measured with a Tramex® CME / CMExpert at must be below 4% before applying the product. This product should not be applied to concrete substrates that show high levels of moisture/humidity unless a moisture a LABPOX MVB moisture mitigation system is used. Although this product may be applied in a wide range of thickness, limitations may apply when taking into consideration curing time. Everything else being equal, thicker is the film, quicker is the curing time. Drying time will be faster in a hot environment. Conversely, the drying time will be longer in a cold environment and the appearance of the surface may be affected. Do not clean the finished surface during the week following installation. Keep the product stored at room temperature to ensure consistent results. Not suited for exterior applications.

Labsurface stands behind the quality of its products. However, Labsurface cannot guarantee results since Labsurface has no control over surface preparation, operating conditions, and application procedures. Clients are solely responsible to test Labsurface’s products to determine if they perform as expected. To meet our strict requirements, we are continuously testing our coatings and on occasion, formulations may be modified to improve certain properties within each coating. Information and data included in this reference document may not be up to date as of the date of reference. Contact Labsurface for further information regarding the limitations of this product.

- + Full color customization available

Refer to the most recent Material Safety Data Sheet prior using this product

Labsurface

101-1079 des Forges, Terrebonne, QC, Canada, J6Y 0J9
Phone: 450-966-9000 / Fax: 450-621-3135
Labsurface.com

Available Colors

Standard Color Chart - Pre-Tint

